

Unraveling the Potassium Storage Mechanism in Graphite

Jilei Liu

College of Materials Science and Engineering, Hunan province key laboratory for advanced carbon materials and applied technology, Hunan University, Changsha, 410082, China

Email: liujilei036@163.com / liujilei@hnu.edu.cn

Potassium-intercalated Graphite intercalation compounds (K-GICs) are of particular physical and chemical interest due to their versatile structures and fascinating properties. Fundamental insights into the K^+ storage mechanism, and the complex kinetics/thermodynamics that control the reactions and structural rearrangements allow manipulating K-GICs with desired functionalities. Here *operando* studies including in-situ Raman mapping and in-situ XRD characterizations, in combination with density-functional theory simulations were carried out to correlate the real-time electrochemical K^+ intercalation/de-intercalation process with structure/component evolution. The experimental results, together with theoretical calculations, reveal the reversible K-GICs staging transition: $C \leftrightarrow \text{stage 5 (KC}_{60}) \leftrightarrow \text{stage 4 (KC}_{48}) \leftrightarrow \text{stage 3 (KC}_{36}) \leftrightarrow \text{stage 2 (KC}_{24}/\text{KC}_{16}) \leftrightarrow \text{stage 1 (KC}_8)$. Moreover, the staging transition are clearly visualized and an intermediate phase of stage 2 with the stoichiometric formula of KC_{16} is identified. The staging transition mechanism involving both intrastage transition from KC_{24} (stage 2) to KC_{16} (stage 2) and interstage transition is proposed. The present study promotes better fundamental understanding of K^+ storage behavior in graphite, develops a nondestructive technological basis for accurately capture non-uniformity in electrode phase evolution across the length scale of graphite domains, and offers guidance for efficient research in other GICs.